

SOURCE

Technical sheet



CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Composition	50% Recycled Sunbrella Acrylic 47% Sunbrella Acrylic 3% Polyester			
Backing / Finish	Non PFAS - Water-repellent & Stain-proof			
Weave	BRAIDED 2/2			ISO 7211-1
Weight	365		g/m ²	ISO 3801
Width	140		cm	EN 1773
Roll length	40		ml	

FABRIC RESISTANCE

Tensile strength	110	80	daN/5cm	ISO 13934-1
Elongation at break	33	28	%	ISO 13934-1
Pilling	5		Class / 5	ISO 12945-2
Spray test	5		Class / 5	ISO 4920
Seam slippage (180 N)	< 0.5	< 0.7	mm	ISO 13936-2
Stitching strength	600	540	N	ISO 13935-2
Stability on 30 deg. C washing	-1.5	-0.3	%	ISO 5077

COLOUR-FASTNESS

Colour fastness UV - outdoor - 1000h	4-5		Class / 5	ISO 105 B04
Colour fastness UV - indoor	8		Class / 8	ISO 105 B02
Colour fastness under dry friction	5		Class / 5	ISO 105X12
Colour fastness under wet friction	5		Class / 5	ISO 105X12
Colour fastness 30°C washing	5		Class / 5	ISO 105 C06

FIRE RESISTANCE

California Technical Bulletin 117-203 Section 1	PASS
NFPA 260 Classe I	PASS
NF EN 1021-1	PASS
BS 5852 Part 1 Source 0	PASS

USES

Guarantee	5	years
Recommended Uses	Seating, Cushions	

CARE



This product's values may vary with a tolerance of $\pm 5\%$

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK



STANDARD 100

CQ 638/10
IFTH

