

SPARK

Technical sheet

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		



GENERAL CHARACTERISTICS

Composition	100% fire-retardant solution dyed polyester			
Backing / Finish	Water-repellent & Stain-proof			
Weave	Canvas			ISO 7211-1
Weight	335.00		GMET	ISO 3801
Thickness	0.60		MM	ISO 5084
Width	120		CM	EN 1773
Roll length	60		ML	

FABRIC RESISTANCE

Tensile strength	220.00	110.00	DAN5	ISO 13934-1
Elongation at break	52	40	%	ISO 13934-1
Tear strength	7.00	2.50	DAN	ISO 13937-1
Stiffness	530	550	MN	ISO 2493
Elongation under load	2	6	%	MO LAB 025
Schmerber	200		MM	ISO 811
Spray test	4		CLA5	ISO 4920
Fire resistance / Euroclasse	Bs1d0			EN 13501-1
Fire resistance / FR	M1			NF P 92 503
Fire resistance / DE	B1			DIN 4102
Fire resistance / IT	C1			UNI 9176
Fire resistance / ES	M-1			UNE 23727 :1990

COLOUR-FASTNESS

Colour fastness UV - outdoor - 1000h	4-5		CLA5	ISO 105 B04
--------------------------------------	-----	--	------	-------------

USES

Guarantee	5		YE	
Recommended Uses	Awnings of all types			

This product's values may vary with a tolerance of $\pm 5\%$

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK

